

TECHNICAL DATA SHEET

General Description

Commercial name:	EnhanceU-T-light
Producer:	Advanced Dispersed Particles S.L
Chemical formula:	TiO ₂ - FeOOH - Fe ₂ O ₃ - SiO ₂ (mixture)
INCI:	Titanium Dioxide, Silica, CI-77492, CI-77491
CAS No.:	113463-67-7, 7631-86-9, 51274-00-1, 1309-37-1
Colour and Form:	Rosy Powder
Type of product:	Mineral UV filter for cosmetics
Other properties:	Colouring of cosmetics

Technical Data – Typical Values


Titanium dioxide	87-95wt. % (X-Ray Fluorescence Analysis)
Silicon dioxide	2-7wt. % (X-Ray Fluorescence Analysis)
Iron oxides	1-4wt. % (X-Ray Fluorescence Analysis)

Metals	Units	Max.	Method
As (Arsenic)	mg/Kg	1	ICP-MS or AA
Cd (Cadmium)	mg/Kg	1	ICP-MS or AA
Hg (Mercury)	mg/Kg	1	ICP-MS or AA
Pb (Lead)	mg/Kg	10	ICP-MS or AA
Sb (Antimonium)	mg/Kg	2	ICP-MS or AA
Zn (Zinc)	mg/Kg	50	ICP-MS or AA
Loss on drying	%	3	Gravimetry
Loss on ignition	%	10	Gravimetry
Solubility in water	%	5	Gravimetry
Solubility in HCl	%	10	Gravimetry

This product is in compliance with Regulation (CE) 1223/2009 on cosmetic products. Traces' metals obey limits for E172 and E171 included in Commission Regulation (EU) No 231/2012 and Spanish Real Decreto No 1465/2009, as well as FDA 21.CFR.73.1200, 21.CFR.73.2250, FDA 21.CFR.73.1575, 21.73.575. Internal specifications are set for loss of water, loss in ignition, and solubility due to the nature of the product (the product is not a pure substance but a mixture).

This product is commercialized based on CSIC License. The manufacturing process is based on a patented technology which is exclusively licensed to Advanced Dispersed Particles, S.L. (ADParticles).

UV Absorption Spectrum



Solar Light SPF-290AS Spectrophotometer.


In vitro measurement:

SPF	UVA PF	UVA/UVB ratio	CW (nm)
51	30	0,78	383

Standard formula. Filter concentration: 15wt%

INCI: Aqua, titanium dioxide, octyldodecyl myristate, isopropyl myristate, paraffinum liquidum, glyceryl stearate, stearic acid, cetyl alcohol, triethanolamine, preservative, silica, CI-77492, CI-77491

In vitro SPF and UVA evaluation. Photostability evaluation.



EnhanceU-T-light filter was included in standard formula at 7.5, 10, 12 or 15% (w/w).

SPF and UVA PF values were obtained from the UV absorption spectra.


Photostability tests were performed to evaluate the protection properties both before and after irradiation of the sample with UV light. After 2 irradiation sessions of 5 and 11 min, the photostability value was higher than 80% and thus the sample considered to be photostable.

Particle size distribution

Average particle size

>0.1µm (DLS, Dynamic light scattering; SEM Microscopy)

DLS, water dispersion



Dispersion: 0.01g/10 mL H₂O,
15min ultrasound bath
Result: Z average: 370nm
(PDI: 0.1)
- batch 01180303C-

Completed and approved by:

Blanca Motos Pérez, Technical Manager

ADVANCED DISPERSED PARTICLES, S.L.
B-86299211
28770 (MADRID)
www.ad-particles.com

Disclaimer:

The information here included is a guide. Every effort has been made to ensure complete and accurate information concerning this document. The information here provided is based on our current knowledge. It does not claim to be complete and it does not exempt the purchaser from performing further analyses prior to internal approval. Liability claims regarding damage caused by the use of any information provided, including any kind of information that is incomplete or incorrect, will therefore be rejected.